

OPULEN

NATURALIS
COLLECTIONS



OPULEN
GOLD

JS126002H
60X120
9 Randomness
FLAT HONED + WHITE GLAZED surface

APPLICATIONS
Interior
Exterior
Wall
Floor
Residential
Commercial

PIEDRA
STONE COLLECTIONS





OPULEN
WHITE

JS126003H
60X120
5 Randomness
FLAT HONED + WHITE GLAZED surface

APPLICATIONS
Interior
Exterior
Wall
Floor
Residential
Commercial

PIEDRA
STONE COLLECTIONS





OPULEN
GREY

JS126005H
60X120
6 Randomness
FLAT HONED + WHITE GLAZED surface

APPLICATIONS
Interior
Exterior
Wall
Floor
Residential
Commercial

PIEDRA
STONE COLLECTIONS



INSTALLATION TIPS

01 Inspect all product prior to installation for any visible defects or unacceptable colour/shade variation. Claims are not accepted after installation.

02 A 1/4" square-notched trowel is suggested for applying the thin-set.

03 Before grouting, allow the mortar base to dry for 24 to 48 hours.

04 The tiles can be cleaned with clear water and/or a neutral liquid cleaner. Apply the cleaning solution to the properly installed tile using a cloth mop or non-abrasive towel. Follow the application with a clear water rinse and wipe dry to prevent film formation.

05 Sealing the tile is not recommanded, and acid cleaning the tile may result in substantial harm to the product; therefore if either of these applications are performed it will specifically void the warranty.

06 INSTALLATION OF RECTANGULAR TILES:
Staggered space should be kept within 10cm to 15cm to compensate for the warpage of rectangular tiles.



07 Tile leveling system to prevent tile lippage is important, especially when dealing with large format tiles. Due to its design, a tile leveling system interlocks the tiles, ensuring that the surface remains smooth and flat while the thinset dries.



TECHINICAL SPECIFICATIONS

DESCRIPTION	STANDARD TEST	MEASUREMENT UNIT	ISO STANDARD REQUIREMENT	WIFI
Length & Width	ISO 10545 - 2	mm	± 0.5% Max	± 0.5% Max
Thickness	ISO 10545 - 2	mm	± 5.0% Max	± 5.0% Max
Sides Straightness	ISO 10545 - 2	mm	± 0.5% Max	± 0.5% Max
Rectangularity	ISO 10545 - 2	mm	± 0.6% Max	± 0.6% Max
Flatness: a) Centre Curvature b) Edge Curvature c) Warpage	ISO 10545 - 2 ISO 10545 - 2 ISO 10545 - 2	mm mm mm	± 0.5% Max ± 0.5% Max ± 0.5% Max	± 0.5% Max ± 0.5% Max ± 0.5% Max
Surface Quality	ISO 10545 - 2	One major area of tiles	≥ 95% free from visible defect	≥ 95% free from visible defect
Water Absorption	ISO 10545 - 3	Mass	≤ 0.5%	0.05%
Modulus of Rupture	ISO 10545 - 4	N/mm2	≥ 35N/mm2	≥ 35N/mm2
Deep Abrasion	ISO 10545 - 6	mm3	≤ 175 mm3	≤ 175 mm3
Surface Abrasion PEI ASTM C1027	ISO 10545 - 7	Visual Check	Manuf. to state Abrasion Class, Cycle Passed	Manuf. to state Abrasion Class, Cycle Passed
Crazing Test	ISO 10545 - 11	Visual Check	Not Applicable for porcelain tiles	Not Applicable for porcelain tiles
Frost Resistance	ISO 10545 - 12	Visual Check	Required	Required
Chemical Resistance (Low Cons.)	ISO 10545 - 13	Visual Check	Manuf. to state	Manuf. to state
Chemical Resistance (Household/Swimming Pool)	ISO 10545 - 13	Visual Check	Max Visible Change On Cut Side	Max Visible Change On Cut Side
Stain Resistance	ISO 10545 - 14	Visual Check	Class 3 Min	Class 3 Min
Coefficient of Friction	ISO 10545 - 17	Manuf. to state	Manuf. to state	Manuf. to state

Each different tiles series is produced to meet different performance requirements. For specific product technical performance, please request from WIFI sales team or their agent or distributor.

Colour Variations: Since the colour reproduction in this printed piece will vary from the actual tile colours, final selection should be made from tile samples. Colour, shade and glaze variations may exist due to the inherent characteristics of porcelain tile.

WIFI CERAMICHE 唯梵

WIFI CERAMICS

No. 13-17, Building A16, International Ceramics and Sanitary Ware City,
Jihua West Road, Nanzhuang Town, Chancheng District, Foshan City
Guangdong Province, China.

+86-757-8252 5001 info@wificeramics.com www.wificeramics.com